

Phase transition between d -wave and anisotropic s -wave gaps in high temperature oxides superconductors

Iksoo Chang¹, Jacques Friedel², and Mahito Kohmoto³

¹*Department of Physics, Pusan National University, Pusan 609-735, Korea*

²*Laboratoire de Physique des Solides, Université Paris-Sud, Centre d'Orsay, 91405 Orsay Cedex, France
unit associated to the CNRS*

³*Institute for Solid State Physics, University of Tokyo, 7-22-1 Roppongi, Minato-ku, Tokyo, Japan*

We study models for superconductivity with two interactions: $V^>$ due to antiferromagnetic(AF) fluctuations and $V^<$ due to phonons, in a weak coupling approach to the high temperature superconductivity. The nature of the two interactions are considerably different ; $V^>$ is positive and sharply peaked at $(\pm\pi, \pm\pi)$ while $V^<$ is negative and peaked at $(0,0)$ due to weak phonon screening. We numerically find (a) weak BCS attraction is enough to have high critical temperature if a van Hove anomaly is at work, (b) $V^>$ (AF) is important to give d -wave superconductivity, (c) the gap order parameter $\Delta(\mathbf{k})$ is constant(s -wave) at extremely overdoped region and it changes to anisotropic s -wave as doping is reduced, (d) there exists a first order phase transition between d -wave and anisotropic s -wave gaps. These results are qualitatively in agreement with preceding works; they should be modified in the strongly underdoped region by the presence of antiferromagnetic fluctuations and ensuing AF pseudogap.

74.20.-z, 74.20.Fg

One of the most significant works in recent condensed matter physics is undoubtedly the discovery of high T_c copper oxides [1]. It seems the high value of T_c can not be understood by the 'classical' BCS theory [2], a large amount of experimental and theoretical works have been performed. In fact, quite a few number of high T_c superconductors(HTSC) are found.

A phase diagram with doping and temperature is very rich, with the antiferromagnetic ordered phase, the superconductive phases – underdoped and overdoped –, a pseudogap region as well as a 'normal' metallic range. Electron doped compounds show a similar succession of AF, superconductive and normal metallic phases, with lower critical temperatures. It is notable that, in common with the classical BCS case, the superconductive state occurs through a condensation of cooper singlet pairing ($\mathbf{k} \uparrow, -\mathbf{k} \downarrow$).

Currently there are many works that ignore phonon-mediated interactions and, in many cases, van Hove anomaly altogether. In these studies one considers mostly interaction due to AF fluctuations. The main justification for these approaches is that the energy scale for magnetic interaction is $\simeq 1000K$ which is somewhat larger than the Debye temperature of $\simeq 300K$. In fact, the solutions of the gap equation with only positive interaction due to AF fluctuations gives $T_c \simeq 100K$ [3,4] which is consistent with the experimental results. However it is not surprising since T_c varies a lot depending on the coupling constants.

On the other hand there are a number of works [5–9] which show enhancement of T_c due to a van Hove anomaly. In most of these investigations, the main purpose is to obtain high critical temperature which is consistent with the T_c observed at optimal doping. Therefore almost all the works except ref.[6] assume that a van Hove anomaly is on the Fermi surface at optimal doping. In

this way the decrease of T_c from the optimal as doping is increased or decreased is natural. However, the systematic computation of doping dependence has not been done. A potentially serious problem of these approaches is that antiferromagnetic (AF) fluctuations which should be important in the underdoped region are not taken into account.

Recently, Friedel and Kohmoto [10] consider the case where the van Hove anomaly is at 'Fermi level' for undoped(half-filling). Besides phonon mediated interaction, one from AF fluctuations is considered. Indeed, it was shown the AF instabilities decrease faster with increasing doping than the effect of the van Hove anomaly on superconductivity [6]. They argue the followings: Phonon or electron mediated weak BCS attraction is enough to have high critical temperature if a van Hove anomaly is at work near enough to the Fermi level. This could apply to electron doped compounds and also to compounds with CuO_2 planes overdoped in holes, where T_c decreases with increasing doping. If phonons dominate, it should lead to an anisotropic but mainly s superconductive gap and probably also in electron doped compounds. A d gap should develop as observed in a number of cases if AF fluctuations are strong enough. In the underdoped range, the observed decrease of T_c with hole doping can be related in all cases to the development of antiferromagnetic fluctuations which produces a magnetic pseudogap, thus lowering the density of states at the Fermi level. The observed mainly d superconductive gap then can be attributed to antiferromagnetic fluctuations.

The essential feature of the BCS theory is the pairing picture. This has been well established in the 'classical' superconductors. Also there is almost no sign of breakdown of this picture in HTSC. However, in order to obtain the so called 'BCS formula', one needs

the approximations: (a) The pairing interaction is weak, (b) The density of states is not too fast varying near the Fermi surface, (c) The pairing interaction is constant within the cutoffs $\pm k_B T_D$ near the Fermi surface and zero otherwise. These approximations lead to the BCS formula: $T_c \simeq 1.13 k_B T_D \exp\{-1/N(0)V\}$, $\Delta(T=0)/k_B T_c \simeq 1.75$, the universal specific heat jump at T_c , the isotope effect with exponent $\alpha = 1/2$ etc.

We assume (a) throughout this work, but (b) is certainly not appropriate as shown below. There is a large enhancement of the density of states close to the van Hove anomalies. The approximation (c) is oversimplified and will be replaced by weakly screened phonon mediated interaction, by AF repulsive interaction, and in addition by both. Therefore we expect that the BCS formula can be violated in experiments, even if the BCS theory with a singlet pairing is correct.

In order to examine the above ideas, we consider a model on the square lattice with specific interactions between electrons and solve the gap equation for general values of hole doping. The effects of pseudogap are *not* taken into account nor the correction due to the small couplings between CuO₂ planes and the ensuing fluctuations of superconductivity near T_c . Then T_c keeps rising while doping decreases. This contrasts with the behavior of HTSC whose T_c decreases and eventually vanishes in underdoped region.

The high T_c oxides have a square lattice of Cu atoms and O atoms in between the Cu atoms (here we neglect the orthorhombic distortion which exists for some HTSC). We take an effective tight-binding picture to consider the Cu sites only, then with effective transfer t , we have the following results.

For undoped compounds, the Fermi level is then a square. Doping by electrons and by holes produce almost square Fermi surfaces with nearly symmetric deviations from the undoped square surface. This fundamental symmetry between electron and hole dopings fits well the general symmetry of the phase diagram observed for electron and for hole doped compounds.

As a result of this geometry the Fermi level sits also near a strong peak in the density of states, which diverges logarithmic at $(\pm\pi, 0)$, $(0, \pm\pi)$ for the undoped compounds. This van Hove anomaly is characteristic of the (quasi) two-dimensional compounds, where it is much stronger than in more isotropic 3d compounds.

The kinetic part of the square lattice model with only nearest-neighbor hopping can be written $\varepsilon(k) \simeq -2t(\cos k_x + \cos k_y)$ where the transfer t is typically 0.25eV and energy will be measured in units of t from now on. In this energy dispersion, there are two saddle points which lead to the van Hove singularities at $(\pm\pi, 0)$ and $(0, \pm\pi)$. The gap equation is

$$\Delta(\mathbf{k}) = -\frac{1}{2} \sum_{\mathbf{k}'} V_{\mathbf{k}\mathbf{k}'} \Delta(\mathbf{k}') \tanh\left(\frac{E_{\mathbf{k}'}}{2k_B T}\right) \frac{1}{E_{\mathbf{k}'}} \quad (1)$$

where $\Delta(\mathbf{k})$ is the gap order parameter, $V_{\mathbf{k}\mathbf{k}'}$

is the interaction between electrons, and $E_k = \sqrt{\{\varepsilon(k) - \mu\}^2 + \Delta(\mathbf{k})^2}$ where μ is the chemical potential.

– *BCS isotropic interaction* $V_{\mathbf{k}\mathbf{k}'} = \text{const.} (= -3t) < 0$. In the overdoped range one can reasonably neglect the effects of AF fluctuations in the 'normal' metallic range. A high critical temperature T_c can then be obtained in the mean field BCS approximation.

The critical temperature is plotted in Fig. 1 for weak coupling region where $N|V| \leq 0.3$ where N is DOS near the bottom of the band. At the bottom of the band $T_c \simeq 10K$ which is quite reasonable for weak coupling BCS theory. It has an exact particle-hole duality. In the extremely overdoped region, the BCS prediction is well satisfied because DOS is not so fast varying within the cutoffs. This is no longer true for lower dopings where DOS is larger and changes rapidly. The enhancement of T_c is considerable there, about 150K at undoped. The gap is s-wave since the interaction is constant. This result shows that weak BCS interaction is enough to have high T_c .

We stress that this enhancement of T_c is only induced by the DOS effect. The coupling does not play any role. It seems that it is not totally unrealistic to expect extremely high T_c like room temperature. However, there exist AF effects near undoped in the all known high T_c superconductors. It is likely to suppresses T_c .




FIG. 1. Critical temperature T_c^μ vs chemical potential for BCS attractive interaction ($V_{\mathbf{k}\mathbf{k}'} = -3t < 0$).

– *Weakly screened phonon-mediated interaction* $V^<$. Let us consider the interaction

$$V_{\mathbf{k},\mathbf{k}'}^< = -\frac{|g_{\mathbf{q}}|^2}{|\mathbf{q}|^2 + |\mathbf{q}_0|^2}, \quad (2)$$

where $\mathbf{q} = \mathbf{k} - \mathbf{k}'$, $g_{\mathbf{q}}$ is the electron-phonon coupling and $2\pi/|\mathbf{q}_0|$ is the screening length. This type of phonon contribution is used in ref.[8,9]. We take a large screening radius about 30 lattice spacing because of poor 2d

screening. The sign of $V_{\mathbf{k},\mathbf{k}'}^<$ is always negative.

Critical temperature is displayed in Fig. 2. The gap $\Delta(\mathbf{k})$ now has an extended s -wave symmetry near half-filling. The new feature is that the gap not only depends on the angle of $\mathbf{k}$ but also on the absolute value $|\mathbf{k}|$ considerably being maximum at Fermi level. See Fig.2(a),(b), and (c). Possibility of this phenomena has not been considered seriously in the past. In most of the previous works on superconductivity, $\Delta(\mathbf{k})$ is computed for $\mathbf{k}$ at the Fermi level.

A notable feature is that T_c does not decrease by doping very much. In this region it is very hard to have pure HTSC samples. Thus it is likely that our results do not apply. For extremely doped region we have also high T_c superconductivity. This behavior will be discussed elsewhere [11].




FIG. 2. Critical temperature T_c for weakly screened phonon-mediated interaction ($V_{\mathbf{k},\mathbf{k}'}^< = -|g_q|^2/(\mathbf{q}^2 + \mathbf{q}_0^2)$), and polar plot of gaps at $T = 0$ for (a) $\mu = -3.6$ (extended isotropic s -gap), (b) $\mu = -2.0$ (slightly anisotropic s -gap), and (c) $\mu = -0.2$ (anisotropic s -gap). The distance from origin is the amplitude of gap for a given angle $\theta = \tan^{-1}(k_y/k_x)$. (d) (1) $\Delta(0)_{max}/k_B T_c$ and (2) $\Delta(0)_{ave}/k_B T_c$ vs μ .

–*AF fluctuation mediated interaction $V^>$* . There are a number of attempt to obtain high T_c within the weak coupling BCS theory only from repulsive interactions which are originated from AF fluctuations [3,4]. Here we take the form of interaction by Monthoux et al. [4] This interaction has peaks at $(\pm\pi, \pm\pi)$. We, however, take much weaker coupling about 1/10 compared with one used by Monthoux et al. [4] (The peak value of their interaction is about 80eV). We obtain relatively low T_c ($T_c \sim 30K$ at undoped) and it vanishes at doping $c \simeq 0.1$. The result obtained by using the coupling of ref.[4] is also confirmed.

This contrasts with attractive interaction which always give superconductivity at low temperature for all doping. The gap is always d -wave for this type of repulsive interaction [10]. Also we do not obtain a gap which breaks the square symmetry like the one studied by ref.[12] even

in low temperatures.

–*The two types of interaction $V^> + V^<$* . Finally we take both interactions into account. The two interactions do not cancel directly since $V^>$ has peaks at $(\pm\pi, \pm\pi)$ and $V^<$ at $(0, 0)$. In any event, the peak of $V_{\mathbf{k},\mathbf{k}'}^>$ is fixed at $(\pm\pi, \pm\pi)$ and the effect of the interaction near Fermi level strongly depends on doping. On the other hand $V_{\mathbf{k},\mathbf{k}'}^<$ does not so much depend on doping. Thus the relative strength of the two interactions changes with doping.

The results are shown in Fig.3. In case both s and d gap can comprise the (mixed) solution of gap equation for a given point (μ, T) in phase space, the gap function is chosen as the one which has the lower free energy. A notable feature is that, although $V^>$ is not more effective for superconductivity, it is very effective for d wave gap. We find a first order transition line between d and anisotropic s -wave gap. The latent heat is also displayed in Fig.3(d). There are experimental results which show a nodeless HTSC [13,14].




FIG. 3. Critical temperatures T_c and the first order phase transition line (dotted line) for the interaction $V^< + V^>$, and polar plot of gaps at $T = 0$ for (a) $\mu = -3.6$ (extended isotropic s -gap), (b) $\mu = -1.0$ (anisotropic s -gap), and (c) $\mu = -0.2$ (d -gap). (d) is the latent heat across the first order transition line. (e) (1) $|\Delta(0)|_{max}/k_B T_c$ and (2) $|\Delta(0)|_{ave}/k_B T_c$ vs μ .

The quantity $|\Delta(0)|_{max}/k_B T_c$ takes the usual BCS value about 1.75 for isotropic region (See Fig.3(e1)). In the anisotropic region it is larger and about 2.5 which is not surprising because the gap is anisotropic and even has nodes in d -wave cases. This ratio with $|\Delta(0)|_{ave}$ averaged over $\mathbf{k}$ is also plotted in Fig.3(e2).

Our model has the particle-hole symmetry, thus we expect that the electron-doped compounds have similar gap structure. Mostly s -gap reported may be anisotropic and there may be a region of d -wave pairing in underdoped region [15].

We also find a novel scaling relation; Namely, the absolute value of average gap function $|\Delta(T)|$ as a function of T for different chemical potentials can be collapsed into

a universal curve by

$$1 - \frac{|\Delta(T)|}{|\Delta(0)|} = f(t/t_{char}) \quad (3)$$

where $t = 1 - T/T_c$ is the reduced temperature and t_{char} is the characteristic reduced temperature for the decay of $1 - |\Delta(T)|/|\Delta(0)|$ as t increases for different chemical potentials, and f is a universal scaling function. Figure 4 shows a good scaling collapse of the rescaled gap functions in terms of t/t_{char} for different chemical potentials. We observe that $|\Delta(T)|$ decreases as T increases by one fashion for μ below -1.4 and by the other fashion for μ above -1.4 (See fig.4(a)). In fact Fig.4(b) shows that there are two different scaling functions for μ below and above -1.4 at which T_c becomes minimum. This universal scaling does not apply for the region of first order phase transition.




FIG. 4. The scaling collapse of rescaled gap functions versus t/t_{char} for different chemical potentials from $\mu = -4.0$ to $\mu = 0.0$. The inset (a) shows $|\Delta(T)|$ vs T for different chemical potentials, which show different decaying behavior as T below and above $\mu = -1.4$. The curves (1), (2) for $\mu = -3.8, -3.6$ decay in the same fashion, but differently from that of the curves (19), (20) for $\mu = -0.2, 0.0$. The inset (b) shows that there are two different scaling functions below and above $\mu = -1.4$.

To conclude, the presence of totally different types of interactions can be expected to lead to rich physics.

We find that the phonon-mediated interaction is enough to have high temperature superconductivity. The role of AF fluctuation is to have the d-wave gap. More importantly it gives the AF pseudogap which we do not take into account by technical difficulties. Probably the most important prediction is the existence of the first order phase transition between d and anisotropic s gaps which may be tested in experiments with clean samples in the overdoped region.

Acknowledgments

It is a pleasure to thank M.T. Béal, B.I. Halperin, Y. Takada, J. Shiraishi for useful discussions. M.K is grate-

ful for the hospitality at Institut Henri Poincare, Paris and Department of Physics, Pusan National University where a part of this paper was written. I.C is grateful to Korea-Japan binational program through KOSEF-JSPS which made his visit to ISSP, Tokyo possible, to SRC program of KOSEF through RCDAMP, and to BSRI98-2412 of Ministry of Education, Korea.

-
- [1] L.G. Bednorz and K.A. Müller, Z. Phys. B**64**, 199 (1986).
 - [2] J. Bardeen, L.N. Cooper, J.R. Schrieffer, Phys. Rev. **106**, 162; **108**, 1175 (1957).
 - [3] T. Moriya, Y. Takahashi, and K. Ueda, J. Phys. Soc. Jpn. **59**, 2905 (1990); T. Moriya and K. Ueda, J. Phys. Soc. Jpn. **63**, 1871 (1994).
 - [4] P. Monthoux, A.V. Balatsky, and D. Pines, Phys. Rev. Lett. **67**, 3448 (1991); P. Monthoux, A.V. Balatsky, and D. Pines, Phys. Rev. B **46**, 114803 (1992).
 - [5] J.E. Hirsch and D.J. Scalapino, Phys. Rev. Lett. **56**, 2732 (1986).
 - [6] J. Friedel, Physica C, **153-5**, 1610(1988); J. Phys: Condens. Matter. **1**, 7757 (1989); Nato Institute on Condensed Matter, Biarritz (1990).
 - [7] D.M. Newns, C.C. Tui, P.C. Pattnaik and C.L. Kane, Comments Cond. Mat. Physics **15** 273 (1992).
 - [8] A.A. Abrikosov, Physica C**222**, 191 (1994); *ibid.* C**244**, 243 (1996).
 - [9] J. Bouvier and J. Bok, Physica C **249**, 117 (1995); 'Gap Symmetry and Fluctuations in High T_c Superconductors' ed. J. Bok, G. Deutscher, D. Pavuna and S.A. Wolf, Plenum Press, New York (1998) NATO ASI Series, Series B Physics **371** 77.
 - [10] J. Friedel and M. Kohmoto, (preprint).
 - [11] Mahito Kohmoto and Iksoo Chang, (unpublished).
 - [12] M.T. Béal and K.Maki, Phys. Rev. B**53**, 5775 (1996); R. Nemeschek et al., The European Phys. J. **5**, 495 (1998).
 - [13] G. Deutscher, N. Ahsaf, D. Goldschmidt, A. Revcholski, A. Vietkin, Physica C**282-287**, 140 (1997).
 - [14] G. Deutscher and R. Maynard, *The Gap Symmetry and Fluctuation in High T_c Superconductors* edited by J. Bok, G. Deutscher, D. Pavuna and S.A. Wolf NATO ASI Series, Series B Physics **371** (Plenum Press, New York 1998) p.15; *ibid.* p.503, NATO Advanced Study Institute Cargès (1997), ed. J.Bok and Pavuna, Plenum Press London(1998) under press.
 - [15] A. Maeda, H. Yasuda and T. Hanaguri, J. Phys. Soc. Jpn.**68**, 594 (1999).